

Features & Benefits

- Excellent water resistance
- Designed for hot and wet environments
- Ease of use – no mixing or heat-cure
- Bonds most materials
- 100% reactive – no solvents

Approval

ISO 10993-5 Cytotoxicity

Description

PERMABOND® 712 is a low viscosity, solvent-free cyanoacrylate adhesive. This product shows a unique resistance underwater or in hot and wet conditions. It provides high adhesion performance on a variety of substrates including metals, plastics and rubbers. It also exhibits excellent thermal resistance and is suitable for continuous use up to 120°C (150°C peak).

Typical Physical Properties of Uncured Adhesive

Chemical composition	Ethyl cyanoacrylate
Appearance	Transparent
Viscosity @ 25°C	100 mPa.s (CP)
Specific Gravity	1.1

Typical Curing Properties

Maximum gap fill	0.15 mm 0.006 in
Fixture time* (0.1 N/mm ² shear strength is achieved)	10 seconds (ABS) 15 seconds (Aluminium) 10 seconds (EPDM) 25 seconds (Mild Steel) 3 seconds (Buna N Rubber) 15 seconds (Nylon 6) 20 seconds (Nylon 6,6) 10 seconds (Phenolic) 15 seconds (PVC)
Full strength	24 hours

*Fixture times can be affected by temperature, humidity and specific surfaces being bonded. Larger gaps or acidic surfaces will also reduce cure speed.


Typical Performance of Cured Adhesive

Shear strength* (ISO 4587)	Mild Steel (gritblasted) 19-24 N/mm ² (2755-3480 psi) Aluminium (gritblasted) 18-23 N/mm ² (2610-3336 psi) Nylon 6 4-6 N/mm ² (580-870 psi) Nylon 6,6 5-7 N/mm ² (725-1015 psi) ABS 5 N/mm ² (725 psi) SF** PVC 6 N/mm ² (870 psi) SF** PC 4 N/mm ² (580 psi) SF**
-------------------------------	---

*Strength results will vary depending on the level of surface preparation and gap.

**SF = Substrate failure.

Hot Strength



**"Hot strength" shear strength tests performed on mild steel. 24-hour cure at room-temperature and conditioned to pull-temperature for 30 minutes before testing.

Permabond® 712 can withstand higher temperatures for brief periods (such as for paint-baking and wave-soldering processes) provided the joint is not unduly stressed.

Thermal Ageing

The table below shows the shear strength retained after thermal ageing. Lap shear specimens were prepared and cured for 72-hours at 23°C, aged at the indicated temperature, and tested at 23°C.

THERMAL AGEING		
Adhesion on abraded mild steel	100 hrs at 120°C	80% strength retention
	500 hrs at 120°C	50% strength retention

The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. **THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.**

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Chemical Resistance

The table below shows the shear strength retained after immersion in water. Lap shear specimens were prepared and cured for 72-hours at 23°C, aged at the indicated condition and tested at 23°C.

WATER (CHEMICAL) RESISTANCE		
Adhesion on abraded mild steel	100 hrs at 60°C	95% strength retention
	1000 hrs at 60°C	75% strength retention

Heat and Moisture Resistance

The table below shows the shear strength retained after heat and moisture ageing. Lap shear specimens were prepared and cured for 72-hours at 23°C, aged at the indicated condition and tested at 23°C.

HEAT & MOISTURE RESISTANCE		
Adhesion on abraded mild steel	170 hrs at 85°C / 85% RH	90% strength retention

Additional Information

This product is not recommended for use in contact with strong oxidizing materials and polar solvents, although will withstand a solvent wash without any bond-strength deterioration. Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene.

Full information can be obtained from the Safety Datasheet.

Storage & Handling

Storage Temperature	2 to 7°C (35 to 45°F)
---------------------	--------------------------------

Allow adhesive to reach room-temperature before opening bottle to prevent condensation inside the bottle which can reduce shelf-life.

Surface Preparation

Surfaces should be clean, dry and grease-free before applying the adhesive. Use a suitable solvent (such as acetone or isopropanol) for the degreasing of surfaces.

Some metals such as aluminium, copper and its alloys will benefit from light abrasion with emery cloth (or similar) to remove the oxide layer.

Directions for Use

1. Apply the adhesive sparingly to one surface.
2. Bring the components together quickly and correctly aligned.
3. Apply sufficient pressure to ensure the adhesive spreads into a thin film.
4. Do not disturb or re-align until sufficient strength is achieved, normally within a few seconds.
5. Any surplus adhesive can be removed with Permabond® CA solvent, nitromethane or acetone.

NB:

712 cannot be used with activators or primers, such as Permabond® CSA or Permabond® Polyolefin Primer (POP).

Video Links

Surface preparation:

<https://youtu.be/8CMOMP7hXjU>



Cyanoacrylate directions for use:

<https://youtu.be/PiPzutdRmsk>



This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

www.permabond.com

- UK: 0800 975 9800
- General Enquiries: +44 (0)1962 711661
- US: 732-868-1372
- Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. **THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.**

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.