

Cyanoacrylates

Permabond cyanoacrylate adhesives bring a wide variety of performance benefits to the production environment. These benefits include joining dissimilar and hard-to-bond materials, quick curing with very strong adhesion and a wide range of viscosities. Permabond one-part cyanoacrylates are a versatile solution for even the most demanding manufacturing and assembly applications

How do Permabond cyanoacrylate adhesives work?

Permabond cyanoacrylate adhesives are one-part adhesives that cure by reacting with minute traces of moisture on the surface of the material being bonded. Permabond cyanoacrylates cure in seconds at ambient temperatures and have been formulated to bond flexible or rigid surfaces made from a wide range of plastics, rubbers or metals.

Permabond cyanoacrylates are available in a range of viscosities and material adhesion capabilities. These adhesives are formulated to bond a variety of porous and non-porous surfaces and to rigid or flexible materials.

Permabond Primers and Accelerators

- ▶ Permabond POP enhances adhesion to polyolefins.
- ▶ Permabond surface activators pre-treat acidic surfaces to facilitate and speed cure. They can also be used post application to quickly cure any exposed cyanoacrylate to eliminate blooming.

Permabond low and medium viscosity cyanoacrylate formulations provide:

- ▶ Superior bonding to plastic, wood and rubber materials.
- ▶ Excellent bond strength when joining metal to plastic, or rubber to metal.
- ▶ Inherent corrosion resistance; protects part assembly from degradation.

Permabond high viscosity cyanoacrylate adhesives provide:

- ▶ Formulations for use in vertical applications or on porous surfaces.
- ▶ Gap filling ability up to 0.5mm (.02in.)
- ▶ Fast, 30-second cure time; speeds production rates.
- ▶ High-strength adhesion, up to 25MPa; shear strength exceeds that of many substrate materials.

Benefits

- ▶ One-part adhesive chemistry speeds application.
- ▶ Join dissimilar materials, such as rubber to metal, with no compromise in bond strength.
- ▶ Cures in seconds at room temperature; eliminates need for costly jigs or ovens; accelerates assembly rates.
- ▶ Gap fill up to 0.5mm (.02in.)
- ▶ Solvent free; non flammable.
- ▶ Superior bond strength; often exceeds that of substrate material.
- ▶ High-temperature resistance of up to 250°C (480°F)
- ▶ Non-blooming, low odour, improves worker comfort.
- ▶ Impact resistant grades increase durability.
- ▶ Water resistant and UV curable grades available.



Grade	Description	Viscosity mPa.s = cP	Maximum Gap Fill (mm) in	Shear Strength Steel (N/mm ²) psi	Set Time Steel in secs	Service Temperature (°C) °F	Availability
101	Low viscosity, penetrating grade	2-3	(0.05) 0.002	(19-23) 2800-3300	3-5	(-55 to +80) -65 to +180	Worldwide
102	General purpose	70-90	(0.15) 0.006	(19-23) 2800-3300	10-15	(-55 to +80) -65 to +180	Worldwide
105	Difficult rubbers (e.g. EPDM)	30-50	(0.10) 0.004	(18-22) 2600-3200	10-15	(-55 to +80) -65 to +180	Worldwide
108	Intermediate gap fill, plastic bonding	400-600	(0.20) 0.008	(20-22) 2900-3200	10-15	(-55 to +80) -65 to +180	Americas & Asia
130UV	UV curing, low viscosity, fluorescing	200	-	(12-17) 1740-2465	30	(-55 to +120) -65 to +250	Worldwide
135UV	UV curing, tack-free, prevents blooming	800	-	(12-17) 1740-2465	30	(-55 to +120) -65 to +250	Worldwide
170	Metal bonding, maximum gap fill	1000-2000	(0.38) 0.015	(23-25) 3300-3600	15-20	(-55 to +90) -65 to +195	Americas & Asia
240	General Purpose	1200-2500	(0.43) 0.017	(21-25) 3000-3600	15-20	(-55 to +80) -65 to +180	Worldwide
268	Fast curing, intermediate gap fill	1200-2400	(0.43) 0.017	(20-22) 2900-3200	10-15	(-55 to +80) -65 to +180	Americas & Asia
712	Water resistant, low viscosity	100	(0.15) 0.006	(19-24) 2755-3480	25	(-55 to +120) -65 to +250	Worldwide
731	Toughened	100-200	(0.15) 0.006	(24-30) 3500-4400	30-50	(-55 to +120) -65 to +250	Worldwide
735	Toughened, black	100-200	(0.15) 0.006	(24-30) 3500-4400	30-50	(-55 to +120) -65 to +250	Worldwide
737	Toughened, black, max. gap fill	2000-4000	(0.50) 0.020	(19-23) 2800-3300	25-30	(-55 to +120) -65 to +250	Worldwide
751	Advanced flexibility	150	(0.15) 0.006	(13) 1885	5	(-55 to +80) -65 to +180	Worldwide
790	Ultra fast cure, wicking type	1-3	(0.05) 0.002	(18-22) 2600-3200	2-3	(-55 to +80) -65 to +180	Americas & Asia
791	Ultra fast cure, low viscosity	30-50	(0.10) 0.004	(18-22) 2600-3200	2-3	(-55 to +80) -65 to +180	Worldwide
792	Ultra fast cure, general purpose	60-125	(0.15) 0.006	(18-22) 2600-3200	2-3	(-55 to +120) -65 to +250	Worldwide
795	Ultra fast cure, general purpose	400-600	(0.18) 0.007	(18-22) 2600-3200	3-5	(-55 to +80) -65 to +180	Americas & Asia
799	Ultra fast cure, maximum gap fill	4000-6000	(0.50) 0.020	(20-22) 2900-3200	5-10	(-55 to +80) -65 to +180	Americas & Asia
801	High temperature resistance	10-15	(0.05) 0.002	(19-23) 2800-3300	10-15	(-55 to +130) -65 to +270	Worldwide
802	High temperature resistance	90-110	(0.15) 0.006	(19-23) 2800-3300	10-15	(-55 to +160) -65 to +320	Worldwide
825	High temp. resistance to 200°C Patented	100-150	(0.15) 0.006	(15-20) 2175-2900	10-20	(-55 to +200) -65 to +390	Worldwide
910®	Metal bonding	70-90	(0.15) 0.006	(23-29) 3300-4200	5-10	(-55 to +90) -65 to +195	Worldwide
910FS	Metal Bonding, wicking type	2-4	(0.05) 0.002	(23-29) 3300-4200	3-5	(-55 to +90) -65 to +195	Americas & Asia
919*	High temp. resistance, wicking	2-6	(0.05) 0.002	(20-22) 2900-3200	10-15	(-55 to +250) -65 to +480	Americas & Asia
920*	High temp. resistance	70-90	(0.15) 0.006	(19-23) 2800-3300	10-15	(-55 to +250) -65 to +480	Worldwide
922*	High temp. resistance, max gap fill	1200-2000	(0.43) 0.017	(19-23) 2800-3300	10-15	(-55 to +250) -65 to +480	Americas & Asia
940	Low odour, low bloom	3-10	(0.05) 0.002	(16-20) 2300-2900	10-15	(-55 to +80) -65 to +180	Worldwide
941	Low odour, low bloom	10-20	(0.08) 0.003	(16-20) 2300-2900	10-15	(-55 to +80) -65 to +180	Worldwide
943	Low odour, low bloom	90-110	(0.15) 0.006	(16-20) 2300-2900	10-15	(-55 to +80) -65 to +180	Worldwide
947	Low odour, low bloom	900-1500	(0.25) 0.010	(16-20) 2300-2900	20-30	(-55 to +80) -65 to +180	Worldwide
2010	Very fast cure, thixotropic	10,000-20,000	(0.50) 0.020	(19-23) 2800-3300	10-15	(-55 to +80) -65 to +180	Worldwide
2011	Non-drip, non sag gel	Gel	(0.50) 0.020	(20-24) 2900-3500	5-10	(-55 to +120) -65 to +250	Worldwide

*To achieve max. temp resistance, a secondary heat cure is required for 919, 920, & 922.

Permabond® Technologies

Anaerobics

Thread lockers, Thread sealants, FIP Gasketmakers, Retaining Compounds

Cyanoacrylates

Instant adhesives, for rapid bonding of metals, plastics, rubber, and more.

Epoxies

Two-part (ET), Single-part (ES), and Modified Technology (MT) grades are available.

MS-Polymers

Single-part, moisture-curing, flexible sealants

Polyurethanes

Two-part room temperature curing adhesives

Toughened Acrylics

Rapid curing, high strength structural adhesives

UV Light Cured Adhesives

For glass, plastic, and metal with dual cure options.



PERMABOND.COM



info.americas@permabond.com

info.europe@permabond.com

info.asia@permabond.com

Americas - 800-640-7599 (732-868-1372)

Europe - 0800 975 9800 (+44 (0) 1962 711661)

Asia + 86 21 5773 4913

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted, however, and no statement herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers, before using any product, make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions. Always refer to current product technical datasheet for most recent and accurate technical information.